

ALEXIT®
BladeRep Pore Filler 6

Data sheet: **491-66**
Technical info:
Gen. techn. info:

1. Introduction/Characteristics ALEXIT-BladeRep Pore Filler 6 is a solvent-free, polyurethane-based pore filler curing into a tack-free film.

This universal pore filler ensures an efficient painting process; manual filling works are reduced to a minimum.

The good levelling properties ensure an efficient closing of pinholes.

Extremely good drawing and sanding properties accelerate the application process, thus leading to a possible reduction of costs.

2. Range of application For use on large-area objects made of GRP

3. Colour Agate grey

4. Substrate pretreatment Very careful sanding of the substrate.

After sanding remove dust carefully with a suitable anti-static cloth.

Before painting it must be ensured that the surface is free from release agents, sanding dust or any other contaminations.

ALEXIT®

BladeRep Pore Filler 6

5. Trade names	Base Material Hardener	ALEXIT-BladeRep Pore Filler 6 ALEXIT-BladeRep Hardener 6
6. Mixing ratio	6 parts by weight 1 part by weight	ALEXIT-BladeRep Pore Filler 6 ALEXIT-BladeRep Hardener 6
	4 parts by volume 1 part by volume	ALEXIT-BladeRep Pore Filler 6 ALEXIT-BladeRep Hardener 6
7. Pot life	at 23°C/73°F	approx. 5 - 10 minutes 100 g mixed material
8. Application	Filling	
9. Drying	at 23°C/73°F	sandable manually: approx. after 2 hours mechanically: approx. after 3 hours
10. Cleaning	Equipment	ALEXIT-Verdünner / Thinner 62
11. Packaging	ALEXIT- BladeRep Pore Filler 6	20 kg, 6 kg net
	ALEXIT- BladeRep Hardener 495-66	6 kg, 1 kg net
	ALEXIT- Verdünner / Thinner 62	25 kg, 5 kg net
	Kit solution consisting of	0,3 kg base material 0,08 kg hardener
12. Storage	Store between 5 - 35°C in original, unopened containers (acc. to DIN EN 3840:2007).	