

ALEXIT®
BladeRep Putty 3

Data sheet: 491-55
Technical info:
Gen. techn. info:

1. Introduction/Characteristics ALEXIT-BladeRep Putty 3 is a solvent-free, polyurethane-based putty curing into a tack-free film.

This universal putty ensures an efficient painting process; manual filling works are reduced to a minimum.

Extremely good drawing and sanding properties accelerate the application process, thus leading to a possible reduction of costs.

2. Range of application For use on large-area objects made of GRP

3. Colour Agate grey

4. Substrate pre-treatment Very careful sanding of the substrate.

After sanding remove dust carefully with a suitable anti-static cloth.

Before painting it must be ensured that the surface is free from release agents, sanding dust or any other contaminations.

ALEXIT®

BladeRep Putty 3

5. Trade names	Base material Hardener	ALEXIT-BladeRep Putty 3 ALEXIT-BladeRep Hardener 3
6. Mixing ratio	6 parts by weight 1 part by weight	ALEXIT-BladeRep Putty 3 ALEXIT-BladeRep Hardener 3
	4 parts by volume 1 part by volume	ALEXIT-BladeRep Putty 3 ALEXIT-BladeRep Hardener 3
7. Pot life	at 23°C/73°F	approx. 5 - 10 minutes 100 g scheduled quantity
8. Application	Filling Pouring	without addition of thinner with special two component mixing system
9. Drying	at 23°C/73°F	sandable manual : after approx. 2 hours mechanical : after approx. 3 hours
10. Cleaning	Material	ALEXIT-Verdünner 62
11. Packaging	ALEXIT- BladeRep Putty 3	20 kg, 6 kg net
	ALEXIT- BladeRep Hardener 3	6 kg, 1 kg net
	ALEXIT- Verdünner 62	25 kg, 5 kg net
	Kit solution consisting of	0,3 kg base material 0,07 kg hardener
12. Storage	In original, unopened containers at a temperature of 5 - 35°C (in acc. with DIN EN 3840:2007).	